

3M™ Scotchkote™ Epoxy Ceramic Surfacer CR 511

Data Sheet and Application Guide

Product Description

Scotchkote Epoxy Ceramic CR 511 has been specifically developed as a 100% solids coating for resurfacing and lining to improve the efficiency of equipment in fluid flow environments.

Product Features

- Combines good application characteristics with good erosion and corrosion resistance.
- Designed for application by brush.
- Provides a low friction surface improving flow rates in pumps etc.
- Designed for resurfacing and lining metal components.
- Meets BS6920 criteria for contact with potable water.

General Application Steps

1. Remove oil, grease and loosely adhering deposits.
2. Abrasive blast clean steel surfaces to NACE No. 2/SSPC-SP10 Near White Metal, ISO 8501:1, Grade SA2½ .
3. Apply Scotchkote Epoxy Ceramic CR511 to the required thickness.
4. Allow to cure.
5. Visually inspect the system for defects.
6. Repair any defects.

Properties

Property	Value
Colour	Light Grey, Blue and Red
Ratio	2:1 By volume 4:1 By weight
Drying & Cure times at 20°C (68°F)	
Useable life	45 mins
Touch Dry	6 hours
Minimum Overcoating	6 hours
Maximum Overcoating	48 hours
Full Cure	7 days
Volume Solids	100%
Film Thickness (Typical)	250 microns (10 mils).
Coverage Rate	2.5m²/kilo at 250 microns (29.5ft²/kilo at 10 mils)
Tensile Shear Adhesion	18Mpa (2500 psi)
Compressive Strength	70Mpa (10000 psi)
Flexural Strength	57Mpa (8100 psi)
Abrasion Resistance	0.08ml loss per 1000 cycles, 1kg load, CS17 Wheel (ASTM D4060)
Tensile Shear Adhesion	17.24 Mpa (2500 psi)



Application Procedures for 3M™ Scotchkote™ Epoxy Ceramic CR 511

Surface Preparation

Surfaces should first be degreased using 3M™ Scotchkote™ 020 Cleaner.

Surfaces should then be abrasive blast cleaned to a minimum NACE No 2/SSPC-SPC10, Near White Metal, ISO 8501:1, Grade Sa2½ or equivalent with a blast profile of 75 microns (3 mil) to give medium blast profile.

Equipment which has become salt impregnated due to service conditions should first be wet blasted then dry abrasive blasted and checked for presence of salts. This process should be repeated until the salts are removed. Alternatively the surface should be sweated using a blow torch or heat gun to bring salts up to the surface. The surface should once again be blast cleaned. This procedure should be repeated until no further impregnated salts are present.

Care should be taken on pitted surfaces to ensure that all contamination is removed from the bottom of all pits.

Product Mixing

Scotchkote Epoxy Ceramic CR 511 is a two component product supplied as a Part A component and a Part B component which must be mixed together immediately prior to use. Stir the contents of the base component, continue stirring and gradually add the total contents of the Part B container, stir the combined mix until completely homogeneous. The mixed material must be used within 45 minutes of mixing at 20°C (68°F). This time will be reduced at higher temperatures and extended at lower temperatures.

Handling and Safety Precautions

Read all health hazard, precautionary and first aid statements found in the Material Safety Data Sheet, and/or product label prior to handling or use.

3M and Scotchkote are trademarks of 3M Company.

Important Notice

All statements, technical information, and recommendations related to 3M's products are based on information believed to be reliable, but the accuracy or completeness is not guaranteed. Before using this product, you must evaluate it and determine if it is suitable for your intended application. You assume all risks and liability associated with such use. Any statements related to the product which are not contained in 3M's current publications, or any contrary statements contained on your purchase order shall have no force or effect unless expressly agreed upon, in writing, by an authorised officer of 3M.

Warranty; Limited Remedy; Limited Liability.

This product will be free from defects in material and manufacture for a period of 12 months from the time of purchase. **3M MAKES NO OTHER WARRANTIES INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF QUALITY OR FITNESS FOR A PARTICULAR PURPOSE.** If this product is defective within the warranty period stated above, your exclusive remedy shall be, at 3M's option, to replace or repair the 3M product or refund the purchase price of the 3M product. **Except where prohibited by law, 3M will not be liable for any loss or damage arising from this 3M product, whether indirect, special, incidental or consequential (including, but not limited to, loss of profits, business and/or goodwill) regardless of the legal theory. For the sake of clarity, nothing in this statement will be deemed to exclude or restrict 3M's liability for death or personal injury arising from its own negligence.**

Application Procedures

Application should not be carried out when air and substrate temperatures are below 7°C nor when relative humidity exceeds 85% or when the surface to be coated is less than 3°C above the dew point.

Scotchkote Epoxy Ceramic CR 511 can be applied by brush or roller, with brush application being preferred for the first coat of a two coat application. Good quality brushes or short to medium pile roller should be used. The product should be worked into the surface to ensure complete wetting of the surface. On deeply pitted surfaces, care should be taken to avoid air entrapment in the pitted areas.

Best application results are obtained with a minimum substrate temperature of 15°C with 20°C being the ideal temperature.

All equipment must be cleaned IMMEDIATELY after use with Scotchkote 020 Cleaner.

Note: Scotchkote Epoxy Ceramic CR 511 is normally applied as a two coat system to achieved a total dry film thickness of 500 microns.

Packaging and Storage

Supplied in 1 and 3 kilo packs

Use within 5 years of date of manufacture. Store in original sealed containers at temperatures between 5°C and 30°C.

Ordering Information/Customer Service

For ordering, technical and product information or to request a copy of the Material Safety Data Sheet, call +44 (0)1609 780170 or fax +44 (0)1609 783762 (Sales) or 788718 (Technical).

For emergencies, please contact +44 (0)1344 858000.



Corrosion Protection Products 3M United Kingdom plc

23 Standard Way Industrial Estate
Northallerton
North Yorkshire DL6 2XA
United Kingdom
Phone: +44 (0)1609 780170
Fax: +44 (0)1609 780438
www.3M.co.uk/scotchkote

Corrosion Protection Products 3M United Kingdom plc

3M Centre
Cain Road, Bracknell
Berkshire RG12 8HT
Phone: 01344 858000
Fax: 01344 857970
www.3M.co.uk

Please recycle. Printed in UK.
© 3M 2010. All rights reserved.
CR511-1010