

# 3M™ Scotchkote™ Urethane Ceramic Rebuild EG 515

## Data Sheet and Application Guide

### Product Description

Scotchkote Urethane Ceramic Rebuild EG 515 has been specifically developed as a 100% solids repair system with a degree of flexibility for rebuilding and resurfacing equipment operating in fluid flow environments.

### Product Features

- Combines good application characteristics with good cavitation and erosion resistance.
- Designed for application by trowel or spatula at thicknesses upto 6mm.
- Provides outstanding protection against impingement.
- Primarily designed for use on propellers, kort nozzles, guide vanes, turbines etc.

### General Application Steps

1. Remove oil, grease and loosely adhering deposits.
2. Abrasive blast clean steel surfaces to NACE No. 2/SSPC-SP10 Near White Metal, ISO 8501:1, Grade SA2½.
3. Apply Scotchkote Urethane Ceramic Rebuild EG 515 to the required thickness.
4. Allow to cure.
5. Visually or electrically inspect the coating for defects.
6. Repair all defects.

### Properties

| Property                                      | Value                                                    |
|-----------------------------------------------|----------------------------------------------------------|
| Colour                                        | Grey                                                     |
| Ratio                                         | 3:1 By volume<br>3:1 By weight                           |
| <b>Drying &amp; Cure times at 20°C (68°F)</b> |                                                          |
| Useable life                                  | 20 mins                                                  |
| Touch Dry                                     | 2½ hours                                                 |
| Hard Dry                                      | 4 hours                                                  |
| Maximum Overcoating                           | 24 hours                                                 |
| Full Cure                                     | 7 days                                                   |
| Volume Solids                                 | 100%                                                     |
| Specific Gravity                              | 1.2                                                      |
| <b>(Average Mixed)</b>                        |                                                          |
| Film Thickness                                | Upto 6mm.                                                |
| Volume Capacity                               | 835cc (53 cu ins) per kilo                               |
| Tensile Strength                              | 20Mpa (2825 psi)                                         |
| Dielectric Strength                           | > 20KV                                                   |
| Abrasion Resistance<br>(ASTM D4060)           | 0.08 ml loss per 1000<br>cycles, 1kg load, CS17<br>wheel |



# Application Procedures for 3M™ Scotchkote™ Urethane Ceramic Rebuild EG 515

## Surface Preparation

Steel surfaces should be abrasive blasted to NACE No. 2/SSPC-SP10 Near White Metal, ISO 8501:1, Grade SA2½. A minimum blast profile of 75-100 microns should be achieved. Where blast cleaning cannot be carried out the surface should be mechanically abraded to remove all loose scale and produce a surface which is clean, dry and free from rust or dust.

When treating existing equipment which may have become salt impregnated due to service conditions, surfaces should first be wet blasted then dry blasted and tested for presence of salts. This process should be repeated until all salts are removed.

## Product Mixing

Scotchkote Urethane Ceramic Rebuild EG 515 is a two component material comprising Part A and Part B components which must be mixed together prior to use.

Add all the contents of the Part B container into the Part A container and mix thoroughly, alternatively measure three volumes of Part A and one volume of Part B into a clean container and mix thoroughly. The two components initially are fluid, but on mixing form a paste material. To ensure thorough mixing, the paste should be transferred to a mixing board and further mixing carried out to produce a streak free material.

The mixed material should be used within 20 minutes of mixing at 20°C (68°F). This time will be reduced at higher temperatures and extended at lower temperatures.

## Application Procedures

Scotchkote Urethane Ceramic Rebuild EG 515 should not be applied when the relative humidity exceeds 90% or when the surface to be coated is less than 3°C above the dew point.

The mixed product should be applied by trowel or spatula and should be applied to give a uniform even thickness.

Ideally Scotchkote Urethane Ceramic Rebuild EG515 should be applied in a single high build coat. If a second coat is required for any reason, overcoating must be carried out within 24 hours of application of the preceding coat. If the overcoating time is extended thorough mechanical abrading or flash blasting of the first coat should be carried out once the coating is hard dry.

Clean all equipment immediately after use with 3M™ Scotchkote™ Thinners PU 71.

## Packaging and Storage

Supplied in 1 kilo packs

Use within 2 years of date of manufacture. Store in original sealed containers at temperatures between 5°C and 30°C.

## Handling and Safety Precautions

Read all health hazard, precautionary and first aid statements found in the Material Safety Data Sheet, and/or product label prior to handling or use.

## Ordering Information/Customer Service

For ordering, technical and product information or to request a copy of the Material Safety Data Sheet, call +44 (0)1609 780170 or fax +44 (0)1609 783762 (Sales) or 788718 (Technical).

For emergencies, please contact +44 (0)1344 858000.

3M and Scotchkote are trademarks of 3M Company.

## Important Notice

All statements, technical information, and recommendations related to 3M's products are based on information believed to be reliable, but the accuracy or completeness is not guaranteed. Before using this product, you must evaluate it and determine if it is suitable for your intended application. You assume all risks and liability associated with such use. Any statements related to the product which are not contained in 3M's current publications, or any contrary statements contained on your purchase order shall have no force or effect unless expressly agreed upon, in writing, by an authorised officer of 3M.

## Warranty; Limited Remedy; Limited Liability.

This product will be free from defects in material and manufacture for a period of 12 months from the time of purchase. **3M MAKES NO OTHER WARRANTIES INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF QUALITY OR FITNESS FOR A PARTICULAR PURPOSE.** If this product is defective within the warranty period stated above, your exclusive remedy shall be, at 3M's option, to replace or repair the 3M product or refund the purchase price of the 3M product. **Except where prohibited by law, 3M will not be liable for any loss or damage arising from this 3M product, whether indirect, special, incidental or consequential (including, but not limited to, loss of profits, business and/or goodwill) regardless of the legal theory. For the sake of clarity, nothing in this statement will be deemed to exclude or restrict 3M's liability for death or personal injury arising from its own negligence.**



### Corrosion Protection Products 3M United Kingdom plc

23 Standard Way Industrial Estate  
Northallerton  
North Yorkshire DL6 2XA  
United Kingdom  
Phone: +44 (0)1609 780170  
Fax: +44 (0)1609 780438  
[www.3M.co.uk/scotchkote](http://www.3M.co.uk/scotchkote)

### Corrosion Protection Products 3M United Kingdom plc

3M Centre  
Cain Road, Bracknell  
Berkshire RG12 8HT  
Phone: 01344 858000  
Fax: 01344 857970  
[www.3M.co.uk](http://www.3M.co.uk)

Please recycle. Printed in UK.  
© 3M 2010. All rights reserved.  
EG515-1010